



TERRACOTTA

QUARRY TILES

NATURAL STONE
AGGLOMERATES
TUMBLED MARBLE
GRANITE
PEBBLES AND
COBBLESTONES

WHAT IT'S FOR

- Stain protection agent for internal and external surfaces
- Protective basecoat applied before the waxing of internal surfaces with rustic or rough finishes

ADVANTAGES

- Does not alter original colour and appearance
- No film forming
- Does not alter terracotta frost resistance: tested by the Bologna Ceramic Centre
- Certified as suitable for use on food contact surfaces
- Excellent for sanded rustic terracotta and tumbled marble

HOW IT'S USED

Do not dilute: Ready to use

Application

*For treatment of exterior pavings: apply the first coat of **Hydrorep** (for natural stone) or **Fila ES/82** (for terracotta) to the dry paving. The following day, brush on an even, continuous coat of **FilaFob**.*

*For indoor use, apply FilaFob with a large brush. The following day, apply one or two coats of the most suitable protective product (**Filalet**, **FilaMatt**, **FilaSatin**, **FilaLongLife**)*

Maintenance:

diluted solution of FilaCleaner

COVERAGE

With one litre:

Terracotta	5/10 m ²
Stone	10/20 m ²

"Coverage rates are approximate and refer to a single coat of the product"

Packaging

1 litre cans in box of 12.
5 litre cans in box of 4.

PRECAUTIONS

• when used indoors, ventilate the premises thoroughly.

COMPOSITION

Blend of synthetic resins dispersed in de-aromatized hydrocarbon solvent.

LABELLING

Symbol

St Andrew's Cross

Risk phrases

Flammable. Harmful: may cause lung damage if swallowed. Repeated exposure may cause skin dryness or cracking.

Safety phrases

Keep out of the reach of children. Keep away from food, drink and animal feeding-stuffs. In case of fire use: earth, sand, chemical powder or foam. If swallowed, do not induce vomiting: seek medical advice immediately and show this container or label

Contains: de-aromatized mineral turpentine.



TECHNICAL INFORMATION

Appearance: transparent liquid

Colour: colourless

Odour: distinctive hydrocarbon solvent odour

Density: 0.785 kg/litre

Flash point: 40° C

The information above reflects our latest technical know-how and is the outcome of ongoing laboratory research and testing. However, some factors are beyond our control. It is essential to integrate our suggestions with your own on-site preliminary tests and check.

Fila accepts no liability for improper use of its products.



24 hours